



# 16th Edition of the QUALICOAT Specifications – Update Sheet – SPEC-US11

<b>Subject:</b>	<b>Various adjustments</b>
<b>Proposal/Request:</b>	Several adjustments and minor corrections are requested/proposed by the General Licences and/or the Secretariat.
<b>QUALICOAT Resolutions</b>	<b>Resolution No. 3/TC 14.05.20</b>
<b>Valid from:</b>	<b>1 July 2020</b>
<b>REFERENCE</b>	<b>CORRECTIONS</b>
<b>2.1 Appearance</b> ( <i>last sentence</i> )	The colour deviation (ISO 11664-4) from the certified RAL <del>GL</del> card shall not be greater than the limit prescribed in Appendix A8.
<b>2.9. Resistance to humid atmospheres containing sulphur dioxide</b> ( <i>first sentence</i> )	<del>ISO 3234</del> <b>ISO 22479</b> (0,2 l SO <sub>2</sub> - 24 cycles). A cross-cut incision with a width of 1 mm shall be made to cut the organic coating down to the metal.
<b>Appendix A10</b> ( <i>row 8 – standard reference</i> )	<del>ISO 3234</del> <b>ISO 22479</b>
<b>Appendix A12 – Colour tolerances after the weathering test for Class 2 organic coatings</b> ( <i>last row, 1st column</i> )	RAL 1038 removed ( <i>as in Class 1 table</i> )

Author: Specifications WG  
Pascale Bellot

Document Code: SPEC-US11  
QQM Section: 7.8.2  
Date Approved: 25.06.2020  
Approved by: Executive Committee  
Valid from: 01.07.2020  
Version: 01  
No. of Pages: 1